



Range: Core Herringbone

Class: 23 / 31

Wear Layer: 0.5

Surface: Deep Registered Embossed

Construction: Modular Multi Layer Rigid Vinyl

PRODUCT SPECIFICATIONS	STANDARD	TEST VALUE
Total thickness	EN ISO 24346	5,0mm (4 + 1 IXPE underlayment)
Wear layer	EN ISO 24340	0,50 mm
Classification	EN ISO 10874	Domestic: 23 Commercial: 31
Total weight	EN ISO 23997	8110 g/m ²
Wear layer binder content	EN ISO 10582	Type I
Abrasion group	EN 660-2	Group T: ≤ 2,00 mm ³
Dimensions	EN ISO 24342	610mm x 122mm 30 planks/box = 2.23m ² 48 boxes/pallet = 107.04m ²
Surface treatment	-	PUR Ecoprotec TM
Locking system	-	UniClic
Bevelled edges	-	Yes

PRODUCT PERFORMANCES	STANDARD	TEST VALUE
Dimensional stability	EN ISO 23999	≤ 0,05 %
Castor chair	ISO 4918	No damage
Furniture leg	EN ISO 24342	No damage
Squareness & straightness	EN ISO 10874	≤ 0,25 mm
Residual indentation	EN ISO 24343-1	≤ 0,10 mm
Impact sound reduction	EN ISO 717-2	ΔLw = 21 dB

Imported and distributed by Wood Innovations Ltd

PRODUCT PERFORMANCES	STANDARD	TEST VALUE
Light fastness	EN ISO 105-B02	≥ 6
Slip resistance	DIN 51130 EN 13893	R10 DS
Resistance to chemicals	EN ISO 26987	Not affected (0)
Thermal resistance	EN ISO 10456	0,054 m² K/W
Curl after exposure to heat	EN ISO 23999	≤ 2 mm
Fire resistance	EN 13501-1	Bfl-s1
Electrical properties	EN 1815	≤ 0.1kV
Resistance against staining	EN 26987	Passed
Underfloor heating suitability	EN 12524	Suitable

ENVIRONMENT	STANDARD	TEST VALUE
TVOC after 28 days (AgBB test) - Indoor air quality	ISO 16000-9	≤ 100µg/m³
VOC emission class (French regulation) - Indoor air quality	ISO 16000-9	A+
Floorscore VOC test - Indoor air quality	ISO 16000-9	Passed
Plasticizer	-	Phthalate-free
Formaldehyde group	EN 717-1	E1
Recyclability	-	100%



Imported and distributed by Wood Innovations Ltd