



PUR Pro

INSULATION AND MOUNTING FOAM

- ✓ Clean and precise application with gun.
- ✓ Fire retardant class B1.
- ✓ Maximum expansion of 20% after application.
- ✓ Minimal expansion pressure.
- ✓ Can be used from -10°C to +30°C.
- ✓ Rot resistant.

Insulate & airtight

Technical Info

- Raw material: polyurethane.
- Skin formation (FEICA TM 1014): 8 minutes.
- Can be cut (FEICA TM 1005): 30 min.
- Curing time: 60 minutes for 30mm thickness at 20°C.
- Density: ± 17 g/l.
- Yield in free space (FEICA TM 1003): ± 45 litres of foam.
- Yield in joint (FEICA TM 1002): 30 meters foam (joint of 2 x 5 cm).
- Shrinkage (FEICA TM 1004): < 5%.
- Post-expansion (FEICA TM 1010): 70 %.
- Cell structure: $\pm 70\%$ closed cells.
- Fire classification: (DIN 4102): B1.
- Pressure resistance (FEICA TM 1011): $\pm 4,0$ N/cm².
- Shear strength (FEICA TM 1012): $\pm 6,5$ N/cm².
- Water absorption (EN 1609): 1% volume.
- Insulating capacity (DIN 52612): 36 mW/m.K.
- Sound insulation (EN ISO 717-1): 58 dB.
- Transport temperature: up to -20°C.
- Product processing temperature: minimum +5°C.
- Substrate processing temperature: -10°C to +30°C.
- Temperature range: -40°C to +90°C.
- Shelf life: 18 months in unopened packaging, kept in a cool, dry place at 20°C and in the upright position.
- Safety measures: Please consult the safety data sheet.

Product

Characteristics

PUR Pro is a fire retardant class B1 PUR foam to be used with Pur Gun for assembly, filling, sealing, insulation, prevention of thermal bridges and soundproofing, etc. PUR Pro adheres to most building materials and can be finished easily: painting, gluing, or plastering, and so on.

Packing

PUR Pro - aerosol 750ml

670005000

Use

- Protect adjacent surfaces.
- Shake well before use and fit in the PUR Gun.
- Optimal adhesion achieved on clean and stable substrate.
- Lightly moisten the substrate to promote adherence and speed up curing.

Allow PUR Pro to reach room temperature before use. Clean freshly spilled PUR Pro and gun with PUR Cleaner. Clean hands with Powerwipes. Remove hardened residues with Remove All. Store upright and close with clamp during transport.

